20

5

## **Claims**

What is claimed is:

1. A radiation detackifiable, thermally stable adhesive composition comprising: a (meth)acrylate copolymer comprising from 85 wt. % to 97.5 wt. % of a (meth)acrylate ester and from 2.5 wt. % to 15 wt. % of a copolymerizable carboxylate monomer;

a multi-functional urethane acrylate oligomer combined with said (meth)acrylate copolymer to provide from 25 parts to 40 parts of said oligomer per 100 parts of said copolymer; and

a thermally stable free radical initiator to conserve adhesive properties at temperatures from about 115°C to about 155°C, said adhesive composition becoming progressively detackified during exposure to ultraviolet radiation.

- 2. A radiation detackifiable, thermally stable adhesive according to claim 1, wherein said thermally stable free radical initiator comprises 1-benzoyl cyclohexanol.
  - 3. A radiation detackifiable, thermally stable adhesive composition according to claim 1, wherein said (meth)acrylate ester is selected from the group consisting of methyl acrylate, ethyl acrylate, propyl acrylate, n-butyl acrylate, isobutyl acrylate, 2-methylbutyl acrylate, 2-ethylhexyl acrylate, 2-ethylhexyl methacrylate, n-octyl acrylate, n-octyl methacrylate, isooctyl acrylate, isooctyl methacrylate, isononyl acrylate, isodecyl acrylate, isobornyl acrylate, vinyl acetate and mixtures thereof.
- 4. A radiation detackifiable, thermally stable adhesive composition according to claim 1, wherein said copolymerizable carboxylate monomer is selected from the group consisting of acrylic acid, methacrylic acid, beta-carboxyethyl acrylate, itaconic acid, crotonic acid, and fumaric acid.

30

20

25

- 5. A radiation detackifiable, thermally stable adhesive composition according to claim 1, wherein said multi-functional urethane acrylate is an aliphatic urethane acrylate oligomer.
- 6. A radiation detackifiable, thermally stable adhesive composition according to claim 1, wherein said multi-functional urethane acrylate is an aromatic urethane acrylate oligomer.
  - 7. A radiation detackifiable, thermally stable adhesive composition according to claim 6, wherein said multi-functional urethane acrylate is a hexafunctional aromatic urethane acrylate oligomer.
  - 8. A clear adhesive coated sheet for supporting a silicon wafer during manufacture of semiconductor micro-chips at elevated temperature, said coated sheet comprising:
    - a transparent film substrate;
    - a radiation detackifiable, thermally stable adhesive composition comprising:
  - a (meth)acrylate copolymer comprising from 85 wt. % to 97.5 wt. % of a (meth)acrylate ester and from 2.5 wt. % to 15 wt. % of a copolymerizable carboxylate monomer;
  - a multi-functional urethane acrylate oligomer combined with said (meth)acrylate copolymer to provide from 25 parts to 40 parts of said oligomer per 100 parts of said copolymer; and
  - a thermally stable free radical initiator to conserve adhesive properties at temperatures from about 115°C to about 155°C, said adhesive composition becoming progressively detackified during exposure to ultraviolet radiation.
  - 9. A clear adhesive coated sheet according to claim 8, wherein said thermally stable free radical initiator comprises 1-benzoylcyclohexanol.
  - A clear adhesive coated sheet according to claim 8, wherein said adhesive sheet has an initial 180° peel adhesion from stainless steel from about 200g/25mm to about 2,500/25mm, said 180° peel adhesion falling to between about 25g/25mm to about

300g/25mm after exposure of said coated sheet to about 400 mJ/cm<sup>2</sup> radiation from a medium pressure mercury arc lamp said coated sheet having a haze level of less than 8, before and after exposure to radiation, as measured using a BYK Gardner HAZEGARD XL-211 tester.

5

A clear adhesive coated sheet according to claim 10, wherein said adhesive sheet 11. has an initial 180° peel adhesion from stainless steel from about 200g/25mm to about 2,500/25mm, said 180° peel adhesion falling to between about 25g/25mm and about 200g/25mm after exposure of said coated sheet to about 400 mJ/cm<sup>2</sup> radiation from a medium pressure mercury arc lamp.

A clear adhesive coated sheet according to claim 8, wherein said (meth)acrylate 12. ester is selected from the group consisting of methyl acrylate, ethyl acrylate, propyl acrylate, n-butyl acrylate, isobutyl acrylate, 2-methylbutyl acrylate, 2-ethylhexyl acrylate, 2-ethylhexyl methacrylate, n-octyl acrylate, n-octyl methacrylate, isooctyl acrylate, isooctyl methacrylate, isononyl acrylate, isodecyl acrylate, isobornyl acrylate, vinyl acetate and mixtures thereof.

20

A clear adhesive coated sheet according to claim 8, wherein said copolymerizable 13. carboxylate monomer is selected from the group consisting of acrylic acid, methacrylic acid, beta-carboxyethyl acrylate, itaconic acid, crotonic acid, and fumaric acid.

25

- A clear adhesive coated sheet according to claim 8, wherein said multi-functional 14. urethane acrylate is an aliphatic urethane acrylate oligomer.
- A clear adhesive coated sheet according to claim 8, wherein said multi-functional 15. urethane acrylate is an aromatic urethane acrylate oligomer.
- A clear adhesive coated sheet according to claim 15, wherein said multi-functional 16. urethane acrylate is hexafunctional aromatic urethane acrylate oligomer. 30